

Description

Freecem® GP is a single component cementitious ready to use powder. On mixing with specified amount of water, it produces a free flow, non shrink, high strength grout which can be used to fill gaps upto 100mm in single pour. Freecem® GP is a combination of Portland cement, selected graded sand fillers and speciality additives. The water demand for mixing is controlled by the combination of all ingredients to ensure controlled expansion and high early strength.

Features & Benefits

- Chloride free formulation to develop high early strength.
- Non-metallic fillers used ensures long term durability without the risk of corrosion and staining.
- Prepacked, pre-batched material supplied in ready to use condition after mixing with specified amount of water at site. Hence site batching is avoided.
- Enhanced rheology ensures optimum contact with the load bearing areas for perfect support.

Primary Application

Freecem® GP is suitable for supporting machine equipment. Commonly used for grouting base plates of boilers, static equipments such as - storage tanks, power generation systems etc. It can also be used for wide range of anchoring application such as- tall masts, transmission towers etc.

Technical properties

The mixed material with water powder ratio of 0.18 upon curing exhibits the following properties :

Physical properties

Flow by BS Cone (mm) -As per BS 890

Initial	220-250
Final (After 15 minutes.)	190-200

Compressive Strength

Without coarse aggregates as per ASTM C109

Age (days)	24 hrs	3 days	7 days	28 days
Min. Compressive Strength (MPa)	25	45	56	65

with coarse aggregate as per BS:1881 (P-116)

% proportion of aggregates of total powder	Min. Compressive Strengths (MPa)			
	24 hrs	3 days	7 days	28 days
50%	40	55	65	75
75%	45	57	68	80
100%	47	60	70	84

Flexural Strength as per ASTM C384

Age (days)	24 hrs	3 days	7 days	28 days
Flexural Strength (MPa)	2.5	6.5	8.0	10.0

Tensile Strength : 3.7MPa @ 28 days as per ASTM C307

Pullout bond Strength @ 28days (Dia of pipe - 90mm; Length of Rod - 200mm)

10mm	8.4MPa
12mm	9.9MPa
16mm	12.6MPa

Setting Time as per IS :4031(Part 5)-1988

Initial	40 minutes
Final	600 minutes

Freshwet density of wet grout : $\approx 2220\text{kg/m}^3$ depending on actual consistency used.

Modulus of Elasticity: 30890MPa as per ASTM C469

Co-efficient of thermal expansion : 0.0001°C as per ASTM C531

Expansion

Plastic Expansion (As per ASTM C827)	3%
Harden Expansion (As per ASTM C1090)	0.003%

Pressure to restrain : $\approx 0.004\text{MPa}$

Specification Clauses

Performance Specification

All grouting work must be carried out using a pre packed chloride free cementitious product which shall be mixed with clean water to achieve the required consistency, without bleeding or segregation. A positive volumetric expansion of 2 - 4% shall occur while the grout is in plastic state by means of gaseous system.

Application Instructions

Preparation

Foundation surface

The substrate surface must be free from oil, grease or any loose material, debarring agents such as laitance, bolt holes and fixing pockets must be blown clean of any dirt or debris.

Wetting

Several hours prior to placing, the concrete substrates should be soaked with fresh water before grouting to saturated surface condition.

Base plate

The surface of the base plate which is likely to come in contact with the grout shall be cleaned thoroughly to remove any possible rusting, oil, mill scales etc. The base plate shall have holes to allow venting of air during grouting operation.

Formwork

The formwork shall be erected as required to be completely leak proof. The joint between the form work and concrete shall be sealed with foam or rubber strips or by any other suitable means. In some cases it may be necessary to provide outlets for draining out the water used for wetting the surface. The form work shall be fixed such that the grout thickness should not exceed 150mm on pouring side and 50mm on all other sides. Air vents shall be provided suitably as required.

Mixing

The grout shall be mixed with powered heavy duty low speed paddle mixer fitted to a drilling machine. To achieve continuous grouting without time lag, availability of enough number of man power shall be ensured before hand. Quantity of clean water for 25 Kgs powder to achieve a flowable consistency shall not be more than 4.5liters±200ml. The water shall be accurately measured and placed in the container, before Freecem® GP powder is added into the container while agitating the mixer. It may take around 5 minutes of mixing to achieve uniform consistency of the grout. The water powder ratio shall not exceed 0.18. Hand mixing shall be avoided

Curing

On completion of the grouting operation and initial set, the grout in the exposed areas shall be cured with water or by Talrakcure® WB curing membrane.

Estimating

Packaging

Freecem® GP is supplied in 25 Kg bag.

Yield

Allowance should be made for wastage when estimating quantities. The approximate yield per 25 kg bag for flowable consistency is about 13 liters.

Storage

Freecem® GP has a shelf life of 6 months if kept in dry store in original, unopened bag. If stored at high temperature and/or high humidity conditions the shelf life may be reduced.

Precautions

Health & Safety Instructions

Freecem® GP is alkaline and should not come in contact with skin or eye. Inhalation of dust during mixing should be avoided. It should never be ingested. However, if it comes into contact with eyes, wash immediately with plenty of water and seek medical treatment. Gloves, goggles and protective clothing should be worn.



Talrak Construction Chemicals Pvt. Ltd.

An ISO 9001:2015 Certified Company

Works:

Plot No. 115-A, 1st Phase. Harohalli Industrial Area,
Kanakapura Taluka - 562 112. Ramanagar Dist.

www.talrak.in

Important note :

Talrak products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Talrak endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

Ref : TCC/TDS/GA02 - R0