Talrak[®] Tenseal XS

Preformed TPE Profiles for exterior / interior expansion joint gap widths ranging from 40mm to 500mm



The Construction Alchemists

Description

Talrak® Tenseal XS is a flexible TPE based preformed profile for sealing expansion joints in concrete and steel structures of different widths.

The system comprises of:

- Pre-compressed/bellowed/plain preformed strip of different widths and lengths
- Adhesive: Epoxy based adhesive for bonding the preformed profiles to the substrate

Features & Benefits

- Easy to install
- ➤ Available in Pre-formed profiles
- Seals Thermal and cyclic load induced moving gaps of widths ranging from 40mm to 500mm
- ➤ Elongation upto 500%
- Excellent waterproofing property
- Efficiently seals joints moving in multiple planes and directions

Primary Application

Essentially used for sealing expansion joints in concrete and steel structures for waterproofing of joints in bridges, roof slabs, joints between twin columns and beams, Metro rail station buildings etc.

Technical Properties

Application Instructions

Surface Preparation

A thorough inspection of the substrate should be done before the application of Talrak* Tenseal XS system. Remove filler materials such as filler boards etc. from the joints if any and clean the concrete surface on either sides of the joints shall be evened out to a width of about 125 mm from the joint edge grinding any protrusions on the concrete surface.

The substrate should be cleaned free from oil, grease and loose particles by means of wire brush. It should also be free from damages and cracks. The surface shall be made dry either by hot air blowing or by wiping completely dry.

Priming

The clean and dry surface shall be provided with Talrak* Tenseal XS Primer, two component epoxy based primer cum sealer.

Mixing: Mix the entire contents of base and hardener tin together with a slow speed paddle mixer until homogeneous mix is obtained.

Application: The mixed material shall be applied immediately using a roller or a soft nylon brush uniformly over the surface.

Profile	Pro la companya di managara		
Suitable for Expansion gaps	≥ 50 mm to ≤ 75 mm	≥ 100 mm to ≤ 250 mm	Up to 500 mm
Thickness	~ 2.5 mm	~ 2.0 mm	1.5 mm
Ultimate tensile strength	10 MPa	7 MPa	4 MPa
Elongation at Break	450% min.	500% Min.	500% Min.
Service Temperature	-20° C to +110° C	-20° C to + 110° C	-20° C to + 110° C
Water resistance	8 bar	6 bar	6 bar
Puncture resistance	Very good	Very good	Very good
Resistance to Weathering	>3000 h	>3000 h	>3000 h

Application of Talrak® Tenseal EP

Bonding of Talrak[®] Tenseal XS to the concrete shall be done using Talrak[®] Tenseal EP, a two component, solvent free thixotropic epoxy based bonding adhesive.

Mixing: Mix the entire contents of base and hardener tin together scrapping down the sides of the containers. Mix until a uniform grey colour is obtained.

Application: Apply masking tape on both sides of the joint to avoid accidental of Talrak® Tenseal EP in the undesired area. This will help earmark the adhesive application.

The mixed adhesive shall be applied within 10 minutes, in two stages. In the first stage the mixed adhesive shall be applied on the substrate which is covered by the lower flank of Talrak® Tenseal XS. In the second stage, the adhesive shall be applied on the concrete substrate in the area covered by the top flank (with perforations) of Talrak® Tenseal XS.

Installation of Talrak® Tenseal XS Tape

The flanks of Talrak® Tenseal XS that will be making contact with the adhesive shall be properly cleaned to remove all loose particles, dirt etc. if any. Measure the exact length of the tape required and align the same into the prepared joint. Apply pressure such that the lower flank properly bonds to the substrate by the adhesive already applied.

In the first stage of application apply Talrak® Tenseal EP, adhesive evenly on the primed substrate of the area that will be covered by the top flank. The applied adhesive is finished smoothly with a flat trowel to a thickness of 2 mm. Avoid the adhesive getting into the joint. Press the upper flank gently into the adhesive, such that a part of it penetrates through the perforations. Allow the adhesive to aircure for about 30-35 minutes. Apply second layer of Talrak® Tenseal EP such that it completely covers the sides of the top flank of the profile. Smoothen the surface with the flat trowel.

Talrak[®] Tenseal XS



The Construction Alchemist

The same procedure should be followed to bond the other side of the joint. It is recommended to do both the sides of the joint together.

It may be necessary to keep some weight on the profile such that it makes proper contact with the concrete surfaces evenly during the process of the initial setting of the adhesive.

Cleaning

Tools and equipment should be cleaned soon after the application using a Talrasol GP.

Estimating Packaging

1. Talrak* **Tenseal XS** is available in the following variants suitable for different joint widths:

Talrak® Tenseal XS50 and Talrak® Tenseal XS75 are available in a special profile

Talrak® Tenseal XS100 and Talrak® Tenseal XS250 are available in 'Bellow Profile'

Talrak[®] Tenseal XS500 is available in plain tape profile All are available in 20 m long rolls

2. Talrak* **Tenseal XS Primer** is supplied in 1.11 and 4.44kg combo pack

Coverage: 5 to 6 m²/kg

3. Talrak* **Tenseal EP** is supplied in 6 kg combo pack Consumption: 3.3kg/m² of mixed material at 2mm thickness

4. Talrasol GP is supplied in 5 and 10 liter cans

The above coverage rates are given for guidance only as actual quantities used will vary with surface conditions of the substrate.

Storage

Talrak® Tenseal XS has no expiry of shelf life. It is recommended to store in protected stacks such that the profiles are not deformed due to its own weight on long term storage.

Talrak® Tenseal XS Primer and Talrak® Tenseal EP has a shelf life of 12 months if kept in dry store in original, unopened containers.

Precautions

Health & Safety Instructions

Some people are sensitive to epoxy resins and solvents. So, gloves, barrier creams, protective clothing and eye goggles should be worn when handling the resin products. If accidental contact occurs, the resin should be removed before it hardens with resin removal cream followed by washing with soap and water. Solvent should not be used. Should eye contamination occur washing with plenty of clean water should be commenced and medical attention should be sought immediately. Good ventilation should be ensured. Smoking while handling/application is prohibited.

Fire

Talrak® Tenseal XS Primer and Talrasol GP are flammable. Adequate ventilation should be ensured. Smoking or use in a naked flame is prohibited.

Flash Point

Talrak® Tenseal XS Primer: 25°C

Talrasol GP:33°C

Talrak Construction Chemicals Pvt. Ltd.

An ISO 9001:2015 Certified Company

Works:

Plot No. 115-A, 1st Phase. Harohalli Industrial Area, Kanakapura Taluka - 562 112. Ramanagar Dist. www.talrak.in

Important note:

Talrak products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Talrak endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

Ref: TCC/TDS/SL07 - R2